



# TECHNICAL DATA SHEET

|                              |  |
|------------------------------|--|
| <b>Product Name:</b>         | Colorlock Two-Part Paver Sealer  |
| <b>Product Numbers:</b>      | CL5, CL2, CL1  |
| <b>Description:</b>          | A two-component protective clear coat for concrete brick pavers, porous stone, brick and most cement surfaces  |
| <b>Suggested Uses:</b>       | For use on all porous concrete and cement surfaces, porous stone, pavers, brick, and decorative finishes.  |
| <b>Additional Uses:</b>      | Concrete curing compound, concrete chatahoochee, and porous stamped concrete.  |
| <b>Colors:</b>               | Clear  |
| <b>Finish:</b>               | Semi-Gloss (1:1 Dilution Rate)   |
| <b>Vehicle Type:</b>         | Urethane   |
| <b>Solvent Type:</b>         | Water  |
| <b>VOC:</b>                  | <50 gm/l   |
| <b>Flash Point:</b>          | Non-Flammable  |
| <b>Weight Per Gallon:</b>    | 8.7 Pounds (Part A), 9.3 Pounds (Part B)   |
| <b>Recommended Dry Time:</b> | At 70 F and 50% relative humidity: Touch – 2 to 6 hours (depending on weather). Recoat – 3 to 6 hours. Surface will be tack free in 3 to 6 hours, ready for foot traffic in 12 to 24 hours and vehicle traffic in 72 hours. Dry times may vary depending on air temperature, wind, and humidity. |
| <b>Coverage:</b>             | Coverage averages depend on the porosity of the surface: Rolling - 300 sq. ft per gallon. Spraying - 400 sq. ft. per gallon.   |

- Limitations:** CAUTION: DO NOT apply in temperatures below 50 F. DO NOT apply to a puddling surface. On excessively hot surfaces, for example direct sunlight on a hot day, drying may occur too rapidly. If this condition exists, we recommend a light misting of the surface with plain water.
- Surface Preparation:** Pavers must be clean, and free of any dirt, stains, and failed sealer. Testing of the surface is recommended to ensure desired results.
- Mixing:** Colorlock is a two-part product. Mix part A with part B before use. It is recommended to mix part A with part B using a paddle mixer attached to a power drill. If using a stirring stick, stir vigorously for a minimum of 2 minutes to ensure a complete induction. Part A is 4 parts and part B is 1 part, no measuring is necessary if activating the complete kit. Once the sealer is mixed, dilute the mixture once again with one part mixed sealer with one part water. Warning: If you use sealer undiluted, a slippery condition may occur.
- Application:** Brush, Roller ( min 3/8" nap ), or spray. DO NOT APPLY excessive pressure on the roller, roll with light to medium pressure. Apply paver sealer evenly and try to minimize puddles or roller trails. Only one coat is required. Do not apply to areas where standing water is evident. Where there is a possibility of slipperiness – DO NOT APPLY THIS PRODUCT. If there has been a skid texture added to the base coat this product may perform properly but all precautions must be taken.
- Pot Life:** 2 hours. Clean spray equipment thoroughly every two hours.
- Packaging:** 1 Gallon Kit, 2 Gallon Kit, and 5 Gallon Kit
- Limitations /Precautions:** Colorlock must be stored in an air tight container. Once container is opened, pour out desired amount and immediately replace the lids. Any mixed material that is not used within 2 to 3 hours must be discarded and a new batch prepared. Do not attempt to save activated materials after 3 hours. Do not pour previously activated materials into a freshly activated batch. Keep out of reach of children. Do not take internally. Applicators should wear protective eyewear, gloves and NIOSH mask if spraying. If swallowed, contact a physician immediately. Limitation of Liability: Technical data is true and accurate to the date of issuance but not subject to change without notice. Our products conform to our quality standards, but no other warranty or guarantee is expressed or implied. Liability, if any, is limited to replacement of product or purchase price. Labor, cost of labor, equipment or consequential damages are excluded.